



# tesa<sup>®</sup> 75515 - Team 4965 Transfer 125µm



## Product Information

125µm double-sided tackified acrylic transfer tape

## Product Description

tesa<sup>®</sup> 75515 - Team 4965 Transfer 125µm is a conformable, tackified acrylic transfer tape with a thickness of 125µm. It is equipped with our proven and well-known tesa<sup>®</sup> 4965 adhesive which is transparent, ageing resistant and has a high initial tack. tesa<sup>®</sup> 75515 - Team 4965 Transfer 125µm therefore offers very good immediate grab to uneven surfaces and is suitable for a wide range of applications, such as lamination of lightweight, thin materials.

Several products are equipped with this unique and high performing tesa<sup>®</sup> 4965 adhesive and together these products make up Team 4965. This double-sided film tape assortment helps to easily select the most efficient tape based on customer demands, products, and processes. Explore the benefits of the full tesa<sup>®</sup> 4965 assortment here: <https://www.tesa.com/en/industry/general-applications/mounting/team-4965-assortment>

## Product Features

- Excellent conformability due to transfer tape design
- Very good initial adhesion to a wide variety of substrates
- Skin contact certification according to ISO 10993-5 and ISO 10993-10
- Very good temperature and humidity resistance
- Good die cutting properties
- Low VOC - measured according to VDA 278 analysis

## Application Fields

tesa<sup>®</sup> 75515 - Team 4965 Transfer 125µm is suitable for mounting and lamination applications of flexible materials and lightweight parts.

Example applications are:

- Mounting of lightweight parts and materials
- Mounting of foams, felts, fabrics and textiles
- Lamination of insulation materials
- Mounting of flooring systems
- Membrane switch mounting
- Splicing



# tesa<sup>®</sup> 75515

## - Team 4965 Transfer 125 $\mu$ m

### Product Information

### Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

### Product Construction

• Type of liner	glassine	• Color	transparent
• Weight of liner	80 g/m <sup>2</sup>	• Color of liner	brown/blue logo
• Backing material	none	• Thickness of liner	70 $\mu$ m
• Type of adhesive	tackified acrylic		

### Properties/Performance Values

• Ageing resistance (UV)	very good	• Temperature resistance long term	100 °C
• Humidity resistance	very good	• Temperature resistance min.	-40 °C
• Tack	good	• Temperature resistance short term	200 °C

### Adhesion to Values

• ABS (initial)	11 N/cm	• PP (initial)	5 N/cm
• ABS (after 14 days)	13 N/cm	• PP (after 14 days)	6.5 N/cm
• Aluminium (initial)	10 N/cm	• PS (initial)	12 N/cm
• Aluminium (after 14 days)	11 N/cm	• PS (after 14 days)	13 N/cm
• PC (initial)	14 N/cm	• PVC (initial)	9 N/cm
• PC (after 14 days)	14.5 N/cm	• PVC (after 14 days)	15 N/cm
• PE (initial)	5 N/cm	• Steel (initial)	14 N/cm
• PE (after 14 days)	6 N/cm	• Steel (after 14 days)	12 N/cm
• PET (initial)	10 N/cm	• Steel (after 3 days)	14 N/cm
• PET (after 14 days)	10 N/cm		

### Additional Information

Liner variants:

- PV12: transparent PET liner (75 $\mu$ m; 105g/m<sup>2</sup>)
- PV20: branded brown paper liner (70 $\mu$ m; 80g/m<sup>2</sup>)

Dimensional stable PV12 PET liner best suitable for applications, shipping and storage with exposure to high humidity conditions.



# tesa<sup>®</sup> 75515 - Team 4965 Transfer 125 $\mu$ m

## Product Information

### Additional Information

Low VOC - measured according to VDA 278 analysis, tesa<sup>®</sup> 75515 does not contain any single substances restricted by the drafted GB regulations (China).

## Disclaimer

tesa<sup>®</sup> products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa<sup>®</sup> product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.

For latest information on this product please visit <http://l.tesa.com/?ip=75515>