

September, 2019

# 3M™ Polyurethane Adhesive Sealant Fast Cure 550

## Product Description

3M™ 500-Series Polyurethane Construction Sealant, Polyurethane Sealant and Polyurethane Adhesive Sealant products are one component, moisture curing products which form permanent elastic bonds. They bond to a wide variety of materials including plastics, metals, fiberglass, and wood. They are formulated to have a wide variety of Shore A hardness, open times, and performance parameters to meet many application needs.



## Product Features:

Feature	3M™ 500-Series Polyurethane Products:					Advantage
	525	540	550FC	551	560	
One component/moisture curing	X	X	X	X	X	<ul style="list-style-type: none"> <li>No mixing</li> <li>Simplifies production</li> </ul>
Bonds dissimilar materials	X	X	X	X	X	<ul style="list-style-type: none"> <li>Gives design flexibility</li> </ul>
Adheres to a wide variety of materials	X	X	X	X	X	<ul style="list-style-type: none"> <li>Multiple uses and design flexibility</li> </ul>
Permanently elastic	X	X	X	X	X	<ul style="list-style-type: none"> <li>Provides long lasting bonds</li> </ul>
Fast curing	-	-	X	X	X	<ul style="list-style-type: none"> <li>Speeds production</li> </ul>
Paintable after cure	X	X	X	X	X	<ul style="list-style-type: none"> <li>Improves appearance</li> </ul>
High tensile strength	X	X	X	X	X	<ul style="list-style-type: none"> <li>Gives high strength bonds</li> <li>Replace rivets and mechanical fasteners</li> </ul>
Low modulus / Low Shore A Hardness	X	X	-	-	-	<ul style="list-style-type: none"> <li>Ideal for sealing</li> <li>Good for bonding material with different coefficients of thermal expansion</li> </ul>
High modulus / High Shore A Hardness	-	-	X	X	X	<ul style="list-style-type: none"> <li>Ideal for bonding</li> <li>Gives high strength bonds</li> </ul>

# 3M™ Polyurethane Adhesive Sealant Fast Cure 550

## Technical Information Note

The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

## Typical Uncured Physical Properties

**Consistency:** Medium Paste

## Typical Mixed Physical Properties

Property	Values		Test Condition
Tack Free Time	50 to 90 min		Room Temperature
Rate of Cure	4 mm per 24 hr	3/16 in per 24 hr	Room Temperature

## Typical Cured Characteristics

Property	Values		Method
Modulus at 100% Elongation	1 MPa	150 lb/in <sup>2</sup>	ASTM D412
Shore A Hardness	45		ASTM C661

## Typical Performance Characteristics

Property	Values		Method
Tensile Strength	3.1 MPa	450 lb/in <sup>2</sup>	ASTM D412
Elongation at Break	>600 %		ASTM D412
Service Temperature Range	-40 to 90 °C	-40 to 194 °F	

Table continued on next page

# 3M™ Polyurethane Adhesive Sealant Fast Cure 550

## Typical Performance Characteristics (continued)

Property	Values		Method
Application Temperature	5 to 35 °C	40 to 95 °F	
UV Resistance	Good		

## Typical Physical Properties

Property	Values		Notes
VOC	29 g/L	0.242 lb/gal	
Approximate Coverage	38 lineal m	126 lineal ft	10.5 oz. [310 mm Cartridge]; 1/8 in (3 mm) bead
Specific Gravity	1.17		
Sagging (ISO 7390)	None		
Water and salt spray resistance	Excellent		

## Compatibility with paints

Water based: yes

Solvent based: test beforehand

# 3M™ Polyurethane Adhesive Sealant Fast Cure 550

## Product Certifications and Listings

	3M™ 500-Series Polyurethane Products:				
	525	540	550FC	551	560
<b>Standard Specification for Elastomeric Joint Sealants</b> ASTM C920, Type S, Grade NS, Class 25	X	X	X	–	–
<b>NSF R2</b> Coating for Use on Structural Surfaces (White and Gray only)	X	–	X	–	–
<b>Federal Railroad Administration</b> Surface Flame Spread ASTM E162 Smoke Generation ASTM E662	–	X	X	–	X
<b>Bombardier SP800-C</b> Toxic Gas Production	–	X	X	–	X
<b>IMO/MED</b> International Maritime Organization	–	X	X	–	–
<b>Leadership In Energy and Environmental Design (LEED)</b> Contributes to LEED credit	X	X	X	X	X

## Typical Environmental Performance

### Temperature Resistance

Long term exposure to temperatures greater than 194°F (90°C) will decrease tensile strength over time. Do not use these products in applications where the temperatures will continuously exceed 194°F (90°C).

## Handling/Application Information

### Application Ideas:

Market	3M™ 500-Series Polyurethane Products:				
	525	540	550FC	551	560
General Industrial	X	X	X	X	X
Construction	X	X	X	X	X
Marine	–	X	X	X	–
Specialty Vehicle	–	X	X	X	X
	Seals expansion joints, construction panels, roofing tiles. Bonds well to concrete.	Seals lap seams on trucks, trains, trailers, etc., and construction panels.	Bonds and seals many diverse materials. Marine deck to hull bonding.	Bonds and seals many diverse materials. 550-type adhesive sealant with longer open time for use in large surface area applications.	Bonds floors, exterior / interior panels, roofs for trucks, trains, trailers, vans, etc.

# 3M™ Polyurethane Adhesive Sealant Fast Cure 550

## Handling/Application Information (continued)

### Application Equipment

#### Cartridge and Sausage Pack:

A variety of applicators are available. Please contact your sales rep for assistance in selecting an applicator.

#### Bulk Dispensing:

A 38:1 ratio dual action piston pump with a ram is suggested. Actual equipment should be designed for your application based on the volume required. Please contact your sales rep or the technical service group to suggest equipment manufacturers (Graco: 1-877-844-7226 or [www.graco.com](http://www.graco.com)).

# 3M™ Polyurethane Adhesive Sealant Fast Cure 550

## Handling/Application Information (continued)

### Directions for Use

#### Surface Preparation:

Surfaces to be sealed or bonded should be clean and dry. Surfaces should be free from grease, mold release, oil, water/condensation, and other contaminants that may affect the adhesion of the sealant. Abrading with 180 to 220 grit abrasive followed by a solvent wipe will improve the bond strength. Suitable solvents include 3M™ Adhesive Remover or methyl ethyl ketone (MEK).\*

\*When using solvents, use in a well ventilated area. Extinguish all sources of ignition in the work area and observe product directions for use and precautionary measures. Refer to product label and MSDS for further precautions. Always pre-test solvent to ensure it is compatible with substrates.

Local and federal air quality regulations may regulate or prohibit the use of these products or surface preparation and cleanup materials. Consult local and federal air quality regulations before using these products.

Note: Alcohol will interfere with the curing process and extra care must be taken when using alcohol as a cleaning solvent to prevent any contact with the sealant.

#### Primer:

Use of a primer is an extra step and cost and will depend on substrates and the final end use. Using primer can improve the corrosion resistance of certain metals as well as improve the durability of the bond when exposed to high humidity conditions. For most applications, high strength bonds on metal can be achieved without the use of a primer. Pre-testing for adhesion is suggested to determine if a primer is needed. Contact your 3M Technical Service representative for primer recommendation and application advice.

#### Application:

Loading the applicator gun: make sure the applicator is set up with correct plunger attachment for cartridge or sausage pack.

Cartridge: Puncture seal in nozzle and remove the pull-tab seal at the bottom of the cartridge. Load into applicator and fix retaining ring (if applicable). Assemble the nozzle (if applicable) and cut to desired size and shape.

Sausage Pack: Make a 1" slit close to the crimp on one end of the sausage pack. Load the sausage pack into the applicator barrel (slit side out). Place the rounded end of the supplied sausage nozzle onto the slit end of the sausage package and fix with retaining ring. Cut nozzle to desired size and shape.

Product should be used within 24 hours after seal is punctured. Dispense product with the nozzle tip in contact with the substrate to insure good gap filling. Bonding must occur within the first 50% of published skin time

Do not apply polyurethane sealants and adhesive sealants on frozen nor wet surfaces. Do not apply over silicone nor in the presence of curing silicone nor hybrid products. Avoid contact with alcohol and solvents during curing.

Sealant can be tooled immediately after applying to give desired appearance.

#### Cleanup:

While sealant is still soft, cleaning can be done with the same solvents used for surface preparation. Avoid cleaning with alcohol as it will interfere with the curing process.

If sealant is already cured, removal is done mechanically with razor knife, piano wire, sanding or 3M™ Scotch-Brite™ Molding Adhesive and Stripe Removal Disc. This disc is available from 3M Automotive Aftermarket Division.

# 3M™ Polyurethane Adhesive Sealant Fast Cure 550

## Storage and Shelf Life

Polyurethane sealants and adhesive sealants must be stored in a controlled environment to maximize shelf life. Store the products in the original unopened containers below 77°F (25C).

When stored at recommended conditions, the shelf life of cartridges and sausage packs is 12 months from the date of manufacture. For 5 and 55 gallon containers, the shelf life is 6 months from date of manufacture.

## Industry Specifications

NFPA 130 test report details (ASTM E162, ASTM E662, BSS 7239, SMP 800-C)

NFPA 130 test report details (ASTM E1354)

## Trademarks

3M and Scotch-Brite are trademarks of 3M Company.

## References

Property	Values	Method
3m.com Product Page	<a href="https://www.3m.com/3M/en_US/company/us/all-3m-products/~/3M-Polyurethane-Adhesive-Sealant-550-Fast-Cure?N=5002385+3293223616&amp;rt=rudmil">https://www.3m.com/3M/en_US/company/us/all-3m-products/~/3M-Polyurethane-Adhesive-Sealant-550-Fast-Cure?N=5002385+3293223616&amp;rt=rudmil</a>	ASTM D3652
Safety Data Sheet (SDS)	<a href="https://www.3m.com/3M/en_US/company/us/SDS-search/results/?gsaAction=msdsSRA&amp;msdsLocale=en_US&amp;co=ptn&amp;q=550FCin">https://www.3m.com/3M/en_US/company/us/SDS-search/results/?gsaAction=msdsSRA&amp;msdsLocale=en_US&amp;co=ptn&amp;q=550FCin</a>	ASTM D3652

## ISO Statement

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001 standards.

## Precautionary Information

Refer to Product Label and Material Safety Data Sheet for health and safety information before using this product. For additional health and safety information, call 1-800-364-3577 or (651) 737-6501.

# 3M™ Polyurethane Adhesive Sealant Fast Cure 550

## Information

**Technical Information:** The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

**Product Selection and Use:** Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

**Warranty, Limited Remedy, and Disclaimer:** Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

**Limitation of Liability:** Except for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.



# 3M™ Polyurethane Adhesive Sealant Fast Cure 550



3M United States  
3M Center  
St. Paul, MN 55144-1000  
800-362-3550  
[www.3M.com](http://www.3M.com)

Please recycle.  
© 3M 2021. All Rights Reserved.

The brands listed above are trademarks of 3M